

## Guest Editorial

## Graphene Oxide Based Materials in Organocatalysis: Opportunities and Challenges

Professor Laksiri Weerasinghe

*Department of Chemistry, Faculty of Applied Sciences, University of Sri Jayewardenepura*

*Email: [laksiri@sjp.ac.lk](mailto:laksiri@sjp.ac.lk)*

Sri Lanka is one of the few countries with commercially significant deposits of vein graphite, which can exceed 99% carbon purity. The highly crystalline structure and purity of Sri Lankan graphite make it particularly suitable for graphene and graphene oxide (GO) synthesis.

Currently, GO and its analogs represent a versatile class of heterogeneous catalysts for organic synthesis. Their high surface area, tunable surface functionality, environmental compatibility, and reusability make them attractive alternatives to conventional homogeneous catalysts. As shown in Figure 1, GO, sulfonated (S-GO), reduced (r-GO), nitrogen-doped graphene N-GO) and graphene-supported metal nano-composites have shown particularly promising performance in oxidation, condensation, multicomponent, cyclization, and coupling reactions, highlighting their growing importance in synthetic organic chemistry.

GO is an effective catalyst for a wide range of organic reactions due to its unique structural and chemical properties. Its two-dimensional sheet-like structure provides an exceptionally high surface

area, allowing efficient adsorption and interaction of reactant molecules. The abundant oxygen containing functional groups, including hydroxyl, epoxy, carbonyl and carboxyl groups, serve as active catalytic sites that can promote acid-catalyzed reactions, hydrogen-bonding interactions, and electron-transfer processes. These functionalities enable GO to activate substrates and stabilize reaction intermediates, thereby enhancing reaction rates and selectivity. Furthermore, GO acts as a heterogeneous catalyst, facilitating easy separation and reuse while minimizing product contamination. Its metal-free nature, low toxicity, environmental compatibility, and ability to operate under mild reaction conditions make it an attractive alternative to conventional homogeneous and metal-based catalysts. Consequently, GO has emerged as a versatile and sustainable catalytic material for numerous organic transformations. As shown in figure 2, Bielawski et al. have reported GO-catalyzed oxidation of aliphatic and benzylic alcohols to their aldehydes and ketones. Various alkynes have also been converted into the corresponding ketones with an excellent yield.




**Figure 1:** Proposed structures of GO, r-GO and S-GO






**Figure 2:** GO catalyze oxidation reactions

Figure 3 summarize some of the key organic reactions reported by various researchers using GO as an efficient catalyst with excellent reusability.


a. Synthesis of amides



b. 2-substituted 1,3-Benzazoles synthesis



c. One-pot synthesis of thioethers



d. Direct Friedel-Crafts Alkylation




Figure 3

In addition to the developments discussed above, our research group has actively contributed to the application of graphene based materials and their analogs in organic reaction catalysis. We have successfully employed these catalytic systems in several synthetically important transformations, including the Pictet Spengler reaction, Ritter reaction, and the synthesis of oxazolines. These studies have demonstrated the potential of graphene derived catalysts to promote efficient and sustainable organic transformations under environmentally benign conditions. The promising results obtained underscore the versatility of graphene based catalytic platforms and support their continued development as green alternatives to conventional catalytic systems.

Despite the significant advantages of GO and analogs in organic catalysis, several limitations continue to hinder its widespread application. One of the primary challenges is the gradual decline in catalytic activity after repeated recycling cycles, which may result from structural degradation, loss of oxygen-

containing functional groups, or surface fouling by reaction intermediates and products. Additionally, the synthesis of GO often exhibits batch to batch variability due to differences in precursor graphite sources, oxidation methods, and processing conditions, leading to inconsistencies in physicochemical properties and catalytic performance. During certain reactions, GO may undergo partial reduction, altering the density and distribution of its functional groups and consequently affecting its catalytic behavior. Furthermore, although GO has demonstrated effectiveness in numerous organic transformations, the detailed catalytic mechanisms remain insufficiently understood for many reactions, limiting the rational design and optimization of GO-based catalysts. Finally, while promising results have been achieved at the laboratory scale, challenges associated with large scale production, process standardization, cost-effectiveness, and long term stability must be addressed before GO catalysts can be widely adopted in industrial organic synthesis.

Future research on GO and its derivatives is increasingly focused on developing advanced catalytic systems with enhanced activity, selectivity, and sustainability. A major area of interest is the design of single atom catalysts supported on graphene based materials, which maximize atomic utilization and provide well-defined active sites for catalytic reactions. The incorporation of heteroatoms such as nitrogen, sulfur, phosphorus, and boron into graphene frameworks is also being extensively explored to tailor electronic properties and create new catalytic functionalities. In addition, graphene derived materials are gaining attention in photocatalytic and electrocatalytic organic synthesis, where their excellent charge transfer characteristics can facilitate energy efficient chemical transformations. Another promising direction involves the utilization of graphene based catalysts for biomass valorization, enabling the conversion of renewable feedstocks into valuable chemicals and fuels. Research is also emphasizing sustainable and solvent free organic transformations in alignment with green chemistry principles, aiming to reduce waste generation and environmental impact. Furthermore, the development of hybrid nanocomposites that combine graphene materials with metal oxides, polymers, and biopolymers is expected to produce multifunctional catalysts

with improved stability, recyclability and catalytic performance, thereby expanding the scope of graphene based catalysis in both academic and industrial applications.

### Conclusion and Future Prospects

Graphene oxide and its analogs represent a versatile class of heterogeneous catalysts for organic synthesis. Their high surface area, tunable surface functionality, environmental compatibility and reusability make them attractive alternatives to conventional homogeneous catalysts. Reported works with GO, r-GO, S-GO and graphene-supported metal nanocomposites have shown particularly promising performance in green and sustainable synthetic organic chemistry.

It is worthy to note that Sri Lanka possesses a rare opportunity to transition from exporting raw graphite to exporting high-value graphene-based materials. The combination of high-purity vein graphite, growing nanotechnology and synthetic organic chemistry expertise and industrial initiatives from organizations such as Sri Lanka Institute of Nanotechnology and Ceylon Graphene Technologies positions the country as a potential regional hub not only for graphene production but also advanced carbon nano-materials synthesis for catalysis.

### References

1. Lorenzo, L.; Bandini, M.; Graphene Oxide as a Mediator in Organic Synthesis: a Mechanistic Focus. *Angew. Chem. Int. Ed.* **2020**, *59*, 20767.
2. Majumdar, B.; Sarma D.; aSarma TK.; Carbocatalytic Activity of Graphene Oxide in Organic Synthesis. Graphene Oxide - Applications and Opportunities, **2018**, 77361.
3. Garg, B.; Ling, Y.-C. Versatilities of graphene-based catalysts in organic transformations. *Green Materials* **2013**, *1* (1), 47-61.
4. Khalili, D.; Banazadeh, A. R. Graphene oxide as a heterogeneous reagent promoted synthesis of 2-substituted 1, 3-benzazoles in water. *Bulletin of the Chemical Society of Japan* **2015**, *88* (12), 1693-1706.
5. Mohammadi, O.; Golestanzadeh, M.; Abdouss, M. Recent advances in organic reactions catalyzed by graphene oxide and sulfonated graphene as heterogeneous nanocatalysts: a review. *New Journal of Chemistry* **2017**, *41* (20), 11471-11497.
6. Hu, F.; Patel, M.; Luo, F.; Flach, C.; Mendelsohn, R.; Garfunkel, E.; He, H.; Szostak, M. Graphene-catalyzed direct Friedel-Crafts alkylation reactions: mechanism, selectivity, and synthetic utility. *Journal of the American Chemical Society* **2015**, *137* (45), 14473-14480.



**Professor Laksiri Weerasinghe** is a trained synthetic organic chemist, currently serving as a Professor in chemistry at the Department of Chemistry, University of Sri Jayewardenepura. He obtained his BSc (Honors) degree in Chemistry from the University of Colombo and his PhD degree from Washington State University, USA. He was a Postdoctoral Fellow at University of Montreal, Canada and also served as a senior research scientist at Sri Lanka Institute of Nanotechnology from 2015-2020.